



Figure 22. Relationship between silicon content of steel and thickness of zinc coating for dipping times of 9 and 3 minutes respectively at 460°C. The curves are average curves. Significant variations can occur between steels with the same Si content, but from different charges. The high reactivity is between 0.05 and 0.12% Si. This called the Sandelin Effect.